











# monocottura in pasta rossa

red body single-firing tiles . monocuisson en pâte rouge

**GRUPPO DI APPARTENENZA: BIIB EN 14411**

SPECIFIC GROUPING: BIIB EN 14411

GRUPE D'APPARTENANCE : BIIB EN 14411

CARATTERISTICA FEATURES CARACTÉRISTIQUE	SIMBOLOGIA SYMBOLICS SYMBOLOGIE	metodo di prova test method méthode d'essai UNI EN	VALORE PRESCRITTO FIXED VALUE VALEUR PRESCRITE	VALORE MEDIO LA FENICE LA FENICE MEAN VALUE VALEUR MOYENNE LA FENICE
dimensione lati dimensions-length and width dimensions des côtés		ISO 10545-2	± 0,6 %	conforme conform conformes
rettilineità dei lati side straightness rectitude des côtés		ISO 10545-2	± 0,5 %	conforme conform conformes
ortogonalità degli spigoli corner squareness orthogonalité des arêtes		ISO 10545-2	± 0,5 %	conforme conform conformes
planarità flatness planéité		ISO 10545-2	± 0,5 %	conforme conform conformes
spessore thickness épaisseur		ISO 10545-2	± 5,0 %	conforme conform conformes
assorbimento d'acqua water absorption absorption d'eau		ISO 10545-3	$6 < E \leq 10 \%$	conforme conform conformes
forza di rottura breaking strength force de rupture		ISO 10545-4	$\geq 800 \text{ N se } sp \geq 7,5 \text{ mm.}$ $\geq 500 \text{ N se } sp < 7,5 \text{ mm.}$	conforme conform conformes
modulo di rottura modulus of rupture coefficient de rupture		ISO 10545-4	$\geq 18 \text{ N/mm}^2$	conforme conform conformes
resistenza al cavillo crazing resistance résistance aux craquelures		ISO 10545-11	PASS	resistente resistant résistant
resistenza alle macchie stain resistance résistance aux taches		ISO 10545-14	min 3	classe 4-5 class 4-5 classe 4-5