












monocottura in pasta bianca

white body single-firing tiles . monocuisson en pâte blanc

GRUPPO DI APPARTENENZA: BIII GL EN 14411

SPECIFIC GROUPING: BIII GL EN 14411

GRUPE D'APPARTENANCE : BIII GL EN 14411

CARATTERISTICA FEATURES CARACTÉRISTIQUE	SIMBOLOGIA SYMBOLICS SYMBOLOGIE	metodo di prova test method méthode d'essai UNI EN	VALORE PRESCRITTO FIXED VALUE VALEUR PRESCRITE	VALORE MEDIO LA FENICE LA FENICE MEAN VALUE VALEUR MOYENNE LA FENICE
dimensione lati dimensions-length and width dimensions des côtés		ISO 10545-2	± 0,5 %	conforme conform conformes
rettilineità dei lati side straightness rectitude des côtés		ISO 10545-2	± 0,3%	conforme conform conformes
ortogonalità degli spigoli corner squaranness orthogonalité des arêtes		ISO 10545-2	± 0,5%	conforme conform conformes
planarità flatness planéité		ISO 10545-2	+ 0,5 % - 0,3 %	conforme conform conformes
spessore thickness épaisseur		ISO 10545-2	± 10,0 %	conforme conform conformes
assorbimento d'acqua water absorption absorption d'eau		ISO 10545-3	> 10 %	conforme conform conformes
forza di rottura breaking strenght force de rupture		ISO 10545-4	600 N	conforme conform conformes
modulo di rottura modulus of rupture coefficient de rupture		ISO 10545-4	15 N/mm ²	conforme conform conformes
resistenza al cavillo crazing resistan resistance aux craquellures		ISO 10545-11	PASS	resistente resistant résistant
resistenza ai prodotti chimici resistance to chemicals resistance aux produits chimiques		ISO 10545-13	B	conforme conform conformes
resistenza alle macchie stain resistance resistance aux taches		ISO 10545-14	min 3	classe 5 class 5 classe 5